

KEPSTAN®

6002 PL

Kepstan® PEKK powder coatings are based on polyether-ketone-ketone, from the polyaryl-ether ketone polymer family. This is our highest performance powder coating which can survive exposure to high continuous use temperatures and corrosive environments while maintaining good abrasion resistance. This Kepstan® PEKK coatings grade can be applied via electrostatic spray or fluidized bed dip.

PROPERTIES	VALUE	UNIT	TEST STANDARD
THERMAL PROPERTIES			
Oxygen Index	38	%	ISO 4589-1/-2
ELECTRICAL PROPERTIES			
Surface Resistivity, 73 °F	1020	Ohm per square	ASTM D257
Dielectric (Electric) Strength	84	kV/mm	IEC 60243-1
	2130	kV/in	
OTHER PROPERTIES			
Density	1270	kg/m³	ISO 1183
	1.27	g/cm³	
POWDER PROPERTIES			
Nature	PEKK	-	ISO 1218
Color	Natural	-	-
Melting Temperature	300 - 305	°C	ISO 1218
	572 - 581	°F	
POWDER COATING PROPERTIES			
Recommended Coating Thickness	50 - 75	µm	-
	0.00197 - 0.00295	in	
Specific Gravity of Coating, 20°C	1.27	-	ISO 1183
Pencil Hardness	5H	-	ECCA T4
Water Absorption, 24h	≤0.6	%	ISO 62-1
Abrasion Resistance, Wheel CS 17, load 1 kg, 1000 cycles	8 - 12	mg	ISO 9352
Dielectric Strength	84	kV/mm	IEC 60243-1
	2130	V/mil	
Surface Resistivity	1020	W	ASTM D257
Fire Resistance on coated panel	V-0	-	UL 94

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 17-11-2022

KEPSTAN®

6002 PL

PROCESSING Coating, Electrostatic Spray, Fluidized Bed Dipping	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
DELIVERY FORM Powder	
REGIONAL AVAILABILITY North America, Europe, Asia Pacific, South and Central America, Near East/Africa	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.